

**KARAKTERISASI SENSOR LIQUEFIED PETROLEUM GAS  
(LPG) DARI BAHAN KOMPOSIT SnO<sub>2</sub>-ZnO**

**SKRIPSI**



**diajukan oleh :**

**MARDALENI  
1410442026**

**Dosen Pembimbing :  
Dr. Elvaswer**

**JURUSAN FISIKA  
FAKULTAS MATEMATIKA DAN ILMU PENGETAHUAN ALAM  
UNIVERSITAS ANDALAS  
PADANG**

**2019**

**KARAKTERISASI SENSOR LIQUEFIED PETROLEUM GAS  
(LPG) DARI BAHAN KOMPOSIT SnO<sub>2</sub>-ZnO**

**SKRIPSI**

**Karya tulis sebagai salah satu syarat  
untuk memperoleh gelar Sarjana Sains  
dari Universitas Andalas**



**JURUSAN FISIKA  
FAKULTAS MATEMATIKA DAN ILMU PENGETAHUAN ALAM  
UNIVERSITAS ANDALAS  
PADANG**

**2019**

## **KARAKTERISASI SENSOR LIQUEFIED PETROLEUM GAS (LPG) DARI BAHAN KOMPOSIT SnO<sub>2</sub>-ZnO**

### **ABSTRAK**

Telah dilakukan karakterisasi sensor gas LPG berbentuk pelet dari bahan komposit SnO<sub>2</sub> dengan ZnO. Pelet sensor gas LPG dibuat dengan komposisi yang berbeda untuk setiap sampel. Pembuatan sensor gas LPG diawali dengan pencampuran bahan, kalsinasi pada suhu 500 °C selama 4 jam, penggerusan, kompaksi dan sintering pada suhu 700 °C selama 4 jam dengan menggunakan reaksi dalam keadaan padat. Sensor gas LPG diuji pada suhu ruang untuk mendapatkan karakteristik *I-V*, menghitung nilai sensitivitas, selektivitas, konduktivitas, waktu respon dan karakterisasi XRD. Berdasarkan pengukuran karakteristik *I-V*, sensitivitas tertinggi pada sampel 30% mol SnO<sub>2</sub> + 70 % mol ZnO yaitu 4,74 pada tegangan 24 Volt. Nilai selektivitas tertinggi terdapat pada sampel 50% mol SnO<sub>2</sub> + 50% mol ZnO yaitu 2,31 pada tegangan 24 volt. Nilai konduktivitas tertinggi dimiliki sampel 30% mol SnO<sub>2</sub> + 70 % mol ZnO yaitu  $12,32 \times 10^{-4}/\Omega \cdot m$  pada lingkungan LPG. Waktu respon sampel 30% mol SnO<sub>2</sub> + 70 % mol ZnO yaitu 48 s pada tegangan 24 Volt. Hasil XRD menunjukkan ukuran kristal 30% mol SnO<sub>2</sub> + 70% mol ZnO yaitu 53,20 nm lebih kecil dibandingkan dengan 100% ZnO dan 100% SnO<sub>2</sub> yaitu 54,48 nm dan 53,21 nm.

Kata Kunci : sensor LPG, SnO<sub>2</sub>-ZnO, sensitivitas, selektivitas, konduktivitas, waktu respon.

# **CHARACTERIZATION OF LIQUEFIED PETROLEUM GAS (LPG) SENSORS FROM SnO<sub>2</sub>-ZnO COMPOSITE MATERIALS**

## **ABSTRACT**

Characterization of LPG gas sensor in the form of pellets made of SnO<sub>2</sub> and ZnO composite was performed. LPG sensor pellets were made with a different composition for every sample. The making of LPG gas sensors begins with mixing of material, calcining at 500 °C for 4 hours, grinding, compacting and sintering at 700 °C for 4 hours using solid state reaction method. LPG gas sensors was tested at room temperature by measuring the characteristics I-V, calculating sensitivity, selectivity, conductivity, response time and morphology. The highest sensitivity was obtained the sample 30% mol SnO<sub>2</sub> + 70% mol ZnO is 4.74 at a voltage of 24 volts. The highest selectivity was obtained the sample 50% mol SnO<sub>2</sub> + 50% mol ZnO is 2.31 at a voltage of 24 Volts. The highest conductivity value was given a sample of 30% mol SnO<sub>2</sub> + 70% mol ZnO is  $12.32 \times 10^{-4} / \Omega \cdot m$  in the LPG environment. The response time of the sample is 30% mol of SnO<sub>2</sub> + 70% mol of ZnO which is 48 s at a voltage of 24 Volts. The XRD results that the crystallite size of 30% mol SnO<sub>2</sub> + 70% ZnO is 53.20 nm smaller than 100% ZnO and 100% SnO<sub>2</sub> is 54.48 nm and 53.21 nm.

Keywords: LPG sensor, SnO<sub>2</sub>-ZnO, sensitivity, selectivity, conductivity, response time

